



TruVis EHL

Product Data Sheet

PRODUCT/CLASS	2-Ethylhexyl laurate; Mono ester of Lauric Acid	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILTY	US. Additional Country Availability information on request.	
MARKET	Industrial, Transportation, Metalworking	
USES/CLAIMS	Base Oil, Additive; Lubricant, Water Miscible, Friction Modifier	
APPLICATIONS	Hydraulic, Grease, 2-Stroke, MWF	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	5.1 cSt	ASTM D445-09
VISCOSITY @ 100°C	1.8 cSt	ASTM D445-09
POUR POINT	-30 °C	ASTM D5950-02
FLASH POINT, COC	185 °C	ASTM D92-05A
SPECIFIC GRAVITY @ 25°C	0.858	ASTM D4052-09
COLOR, PT CO	40	ASTM D1209-05
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.10 mg KOH/g	ASTM D974-08
MOISTURE CONTENT	500 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

Customer Service:
 1-800-554-9887
 Fax: 401-724-6250



Teknor Apex Company
 505 Central Avenue
 Pawtucket, Rhode Island 02861
www.teknorapex.com/truvis

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.