



TruVis P60100

Product Data Sheet		
PRODUCT/CLASS	Penta/Dipentaerythritol ester; PE-DiPE Polyol Ester	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILTY	US. Additional Country Availability information on request.	
MARKET	Industrial	
USES/CLAIMS	Base Oil; Lubricant	
APPLICATIONS	Refrigeration Compressor	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	93.4 cSt	ASTM D445-09
VISCOSITY @ 100°C	10.6 cSt	ASTM D445-09
VISCOSITY INDEX	96	
POUR POINT	- 37 °C	ASTM D5950-02
FLASH POINT, COC	262 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS	TBD	ASTM D5800A
SPECIFIC GRAVITY @ 20°C	0.973	ASTM D4052-09
COLOR	1.0	ASTM D1500
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.01 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY	TBD	ASTM D2619
MOISTURE CONTENT	30 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

Customer Service:
 1-800-554-9887
 Fax: 401-724-6250



Teknor Apex Company
 505 Central Avenue
 Pawtucket, Rhode Island 02861
www.teknorapex.com/truvis

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.