

# PROCESSING GUIDE FOR EXTRUSION OF FIREGUARD® 910 SERIES JACKETING COMPOUNDS

EQUIPMENT & CONDITIONS	SUGGESTIONS						
<b>Compound Drying</b>	Recommended. Typical condition 170°F for 4 hours minimum.						
<b>Color Concentrate</b>	PVC-based color concentrates used at 2% or less.						
<b>Machine Type</b>	Typical PVC extrusion equipment.						
<b>Screw Design</b>	<p>A) Metering Type, with shallow flights and long metering section</p> <table data-bbox="610 800 959 909"> <tr> <td>Metering Section</td> <td>50%</td> </tr> <tr> <td>Transition Section</td> <td>25%</td> </tr> <tr> <td>Feed Section</td> <td>25%</td> </tr> </table> <p>B) Barrier Maddock (spiral preferred) screw designed for semi-rigid PVC.</p> <p>C) Spirex barrier screw with Pulsar® mixer.</p>	Metering Section	50%	Transition Section	25%	Feed Section	25%
Metering Section	50%						
Transition Section	25%						
Feed Section	25%						
<b>Compression Ratio</b>	2.75:1 CR target (2.5:1 to 3.0:1 range)						
<b>L/D Ratio</b>	24:1 target (20:1 to 24:1 range)						
<b>Screen Packs</b>	20/40/60 typical (up to 80 mesh OK)						
<b>Screw RPM</b>	30 RPM minimum (choose extruder size to accommodate this)						
<b>Screw Cooling</b>	Not Recommended.						
<b>Water Bath</b>	Cold water; 40°F-60°F						
<b>Tooling</b>	<p><b>Cross-head:</b> Low inventory cross-heads.</p> <p><b>Die Design:</b> Tube (Sleeving) type. Matched tip and die angle for equal flow and fairly tight together for optimum die pressure.</p> <p><b>Tube Die:</b> DDR 1.5 - 2.5:1. DBR 1.0 target. 3/32" land length.</p>						

# PROCESSING GUIDE FOR EXTRUSION OF FIREGUARD® 910 SERIES JACKETING COMPOUNDS

## EQUIPMENT & CONDITIONS

## SUGGESTIONS

### Machine Temperatures

Hardness Range	Typical Barrel Settings	Melt Temperature Range
Shore C79 - 85	320°F - 365°F	380°F - 385°F
Shore C86 - 90	340°F - 375°F	385°F - 390°F

\*\*Melt temperature should be measured using a pyrometer on the material exiting the cross-head.

### Purging

If necessary, use HD polyethylene.

### Regind

Not recommended.

### Additional Considerations

Care must be taken to avoid excessive temperatures or delays during extrusion; material should not sit for more than 15 minutes under any circumstances.

Never leave in extruder at elevated temperature without purging.

Never process with an actual melt temperature > 400°F.

**\*\*Do not set any temperature zone above 375°F.**

*The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgment of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.*



### North America

505 Central Avenue  
Pawtucket, RI 02861  
+1-401-725-8000  
1-800-554-9892

### Singapore

41 Shipyard Road  
Singapore 628134  
+65-62652544

### China

Room 1003,  
Lujiazui Finance Plaza  
No. 1217, Dongfang Road  
Pudong, Shanghai 200127  
+86-21-50108083