



TruVis A85

Product Data Sheet		
PRODUCT/CLASS	Di-isooctyl adipate (DIOA); Diester	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILITY	US. Additional Country Availability information on request.	
MARKET	Industrial, Transportation, Metalworking	
USES/CLAIMS	Base Oil; Lubricant	
APPLICATIONS	Gear, Hydraulic, Compressor, Grease, Engine, Axle, 2/4 Stroke, MWF	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	9 cSt	ASTM D445-09
VISCOSITY @ 100°C	2.7 cSt	ASTM D445-09
VISCOSITY INDEX	144	
POUR POINT	- 54 °C	ASTM D5950-02
FLASH POINT, COC	190 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS	33.1	ASTM D5800A
SPECIFIC GRAVITY @ 20°C	0.929	ASTM D4052-09
COLOR, PT CO	50	ASTM D1209-05
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.05 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY	+ 0.09 mgKOH/g Δ	ASTM D2619
MOISTURE CONTENT	500 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.0 mg/L	

Customer Service:
 1-800-554-9887
 Fax: 401-724-6250



Teknor Apex Company
 505 Central Avenue
 Pawtucket, Rhode Island 02861
www.teknorapex.com/truvis-esters

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.