



# TruVis TM350

## Product Data Sheet

<b>PRODUCT/CLASS</b>	Hexyl trimellitate; Diester	
<b>MANUFACTURING LOCATION</b>	Brownsville, Tennessee	
<b>AVAILABILITY</b>	US. Additional Country Availability information on request.	
<b>MARKET</b>	Industrial, Transportation	
<b>USES/CLAIMS</b>	Base Oil; Lubricant	
<b>APPLICATIONS</b>	Gear, Compressor, Chain, Grease	
<b>PROPERTY</b>	<b>TYPICAL VALUE</b>	<b>TEST METHOD</b>
VISCOSITY @ 40°C	34 cSt	ASTM D445-09
VISCOSITY @ 100°C	5.7 cSt	ASTM D445-09
VISCOSITY INDEX	99	
POUR POINT	- 60 °C	ASTM D5950-02
FLASH POINT, COC	245 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS	3.29	ASTM D5800A
SPECIFIC GRAVITY @ 20°C	1.014	ASTM D4052-09
COLOR, PT CO	100	ASTM D1209-05
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.10 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY	+ 0.02 mgKOH/g Δ	ASTM D2619
MOISTURE CONTENT	500 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

**Customer Service:**  
1-800-554-9887  
Fax: 401-724-6250



**Teknor Apex Company**  
505 Central Avenue  
Pawtucket, Rhode Island 02861  
[www.teknorapex.com/truvis-esters](http://www.teknorapex.com/truvis-esters)

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.