

FIREGUARD® 910A-20-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America
Features	• Flame Retardant	• Low Smoke Emission
Uses	• Insulation, Plenum Cable	• Plenum Cable Jacketing
Agency Ratings	• UL 13 • UL 1424	• UL 444 • UL QMTM2
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.	
Appearance	• Colors Available	• Opaque
Forms	• Pellets	
Processing Method	• Wire & Cable Extrusion	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.61	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	15.9	MPa	ASTM D638
Tensile Elongation (Break)	240	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore C, 10 sec, Hand Held	86		
Shore D, 10 sec, Operating Stand	60		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	90.0	°C	ASTM D794
Brittleness Temperature	-10.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (50°C)	5.5E+12	ohms·cm	ASTM D257
Dielectric Constant			ASTM D150
1 kHz	4.38		
1 MHz	3.50		
Dissipation Factor			ASTM D150
1 kHz	0.056		
1 MHz	0.034		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	49	%	ASTM D2863

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

FIREGUARD® 910A-20-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Dynamic Heat Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition): 49..... ASTM D2538

Kayeness ACR @177°C. 1000 sec-1 (Pa-sec): 335..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO-5660

- Peak Heat Release Rate (kW/m²): 111.3
- Average Heat Release Rate (kW/m²): 62.1
- Total Heat Released (MJ/m²): 76.4
- Average Heat of Combustion (MJ/kg): 11.8
- Average Specific Extinction Area (m²/kg): 259
- Peak Smoke (l/m): 1.63

Data Sheet Applies to Colors Listed Below:

Natural (1011214)

Blue 2048 (1041642)

Blue 2108 (1057234)

White 1378 (1057233)

12/23-1c

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	196	°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
<i>In U.S. for Vinyls, TPEs, Colorants,</i>	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
<i>Engineered Thermoplastics (Chem Polymer)</i>	6167 RD Geleen, Netherlands	Suzhou Industrial Park	Singapore 628134
505 Central Avenue		Jiangsu, China 215126	
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950	Phone: (86) 512-6287-1550	Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Fax: (86) 512-6288-8371	Fax: (65) 6265-1821
Phone: 401-725-8000	www.teknorapex.com	www.teknorapex.com	www.teknorapex.com
Fax: 401-725-8095	tpe@teknorapex.com	infotaap@teknorapex.com	infotaap@teknorapex.com
Toll Free (U.S. only) 800-556-3864			
www.teknorapex.com			
info@teknorapex.com			

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.