🚸 TEKNOR APEX

FIREGUARD® 910A-10-NL2H

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information						
General						
Material Status	Commercial: Active					
A 11 1 112	Africa & Middle East	Latin America				
Availability	Asia Pacific	North America				
Features	Flame Retardant	Low Smoke Emission				
Uses	Insulation, Plenum Cable	Plenum Cable Jacketin	ıg			
Agency Ratings	• UL 13	• UL 444				
	• UL 1424	UL QMTM2				
Regulatory Statement		o regulations, specifically, California Proposition 65, EU REACH SVHCs, and Apex for the most up to date compliance statement, or refer to section 15 of the				
Appearance	Colors Available	• Opaque				
Forms	• Pellets					
Processing Method	• Wire & Cable Extrusion					
	ASTM & IS	O Properties ¹				
Physical		Nominal Value	Unit	Test Method		
Density / Specific Gravity		1.62	g/cm ³	ASTM D792		
Mechanical		Nominal Value	Unit	Test Method		
Tensile Strength (Break)		13.5	MPa	ASTM D638		
Tensile Elongation (Break)		170	%	ASTM D638		
Hardness		Nominal Value	Unit	Test Method		
Durometer Hardness (Shore C, 10 sec,	Hand Held)	85		ASTM D2240		
Fhermal		Nominal Value	Unit	Test Method		
Continuous Use Temperature		75.0	°C	ASTM D794		
Brittleness Temperature		-10.0	°C	ASTM D746		
Electrical		Nominal Value	Unit	Test Method		
Dielectric Constant				ASTM D150		
1 kHz		4.81				
1 MHz		3.61				
Dissipation Factor				ASTM D150		
1 kHz		0.071				
1 MHz		0.10				

Flammability

Oxygen Index

Revision Date: 5/22/2024

Test Method

ASTM D2863

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Nominal Value Unit

44 %

Copyright © 2024 UL Prospector

FIREGUARD® 910A-10-NL2H Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Dynamic Heat Stability @ 205°C, 100 RPM, 72 gr. #5 Bowl (Mins. to Decomposition) : 60..... ASTM D2538

Kayeness ACR @ 370°F, 1000 sec-1 (Pa-sec) : 209..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660

- Peak Heat Release Rate (kW/m^2) : 123.5
- Average Heat Release Rate $(kW/m^2): 81$
- Total Heat Released (MJ/m^2) : 62.3
- Average Heat of Combustion (MJ/kg) : 10.3
- Average Specific Extinction Area (m²/kg) : 333
- Peak Smoke (1/m): 2.0

Data Sheet Applies to Color Listed Below: Natural (0131281)

10/19-lc

	Processing Information				
Extrusion	Nominal Value Unit				
Melt Temperature	196 °C				

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.	
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road	
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134	
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950 Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Phone: (65) 6265-2544 Fax: (65) 6265-1821	
Phone: 401-725-8000		Fax: (86) 512-6288-8371		
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com	
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com	
www.teknorapex.com				
info@teknorapex.com				

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.