

Continuous Use Temperature

Dissipation Factor (1 MHz)

Brittleness Temperature

Electrical

Flammability

Oxygen Index

# FIREGUARD® 910A-26 UVF-NL

### Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

Teknor Apex Company - Flexible Polyvinyi Chloride			Saturday, September 14, 2024	
	General I	nformation		
General				
Material Status	• Commercial: Active			
Availability	<ul> <li>Africa &amp; Middle East</li> </ul>	<ul> <li>Latin America</li> </ul>		
	Asia Pacific	North America		
Features	• Flame Retardant	<ul> <li>Low Smoke Emission</li> </ul>		
	<ul> <li>Fungus Resistant</li> </ul>	<ul> <li>UV Resistant</li> </ul>		
Uses	• Insulation, Plenum Cable	<ul> <li>Plenum Cable Jacketin</li> </ul>	ng	
Agency Ratings	• UL 13	• UL 444		
	• UL 1424	• UL QMTM2		
Regulatory Statement	<ul> <li>Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.</li> </ul>			
Appearance	<ul> <li>Colors Available</li> </ul>	<ul> <li>Opaque</li> </ul>		
Forms	• Pellets			
Processing Method	Wire & Cable Extrusion			
	ASTM & IS	O Properties <sup>1</sup>		
Physical		Nominal Value	Unit	Test Method
Density / Specific Gravity		1.61	g/cm³	ASTM D792
Mechanical		Nominal Value	Unit	Test Method
Tensile Strength (Break)		16.6	MPa	ASTM D638
Tensile Elongation (Break)		210	%	ASTM D638
Hardness		Nominal Value	Unit	<b>Test Method</b>
Durometer Hardness (Shore C, 10 sec, Hand Held)		89		ASTM D2240
Thermal		Nominal Value	Unit	Test Method

75.0 °C

-6.00 °C

51 %

Nominal Value Unit

Nominal Value Unit

0.038

Revision Date: 5/22/2024

ASTM D794

ASTM D746

**Test Method** 

ASTM D150

**Test Method** 

**ASTM D2863** 

## FIREGUARD® 910A-26 UVF-NL

#### Teknor Apex Company - Flexible Polyvinyl Chloride

#### **Additional Information**

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition): 54..... ASTM D2538

Kayeness ACR @177°C. 1000 sec-1 (Pa-sec): 310.....ASTM D3835

Cone Calorimeter @ 75 kW/m2 ..... ISO5660
• Peak Heat Release Rate (kW/m²): 119.3
• Average Heat Release Rate (kW/m²): 59.3

• Total Heat Released (MJ/m²): 72.3

Average Heat of Combustion (MJ/kg): 10.9
 Average Specific Extinction Area (m²/kg): 234

• Peak Smoke (1/m): 1.6

Data Sheet Applies to Colors Listed Below: Natural (1021545) Black 1 (1038067)

10/19-lc

**Extrusion** 

Processing Information

Nominal Value Unit

Melt Temperature 196 °c

#### Notes

info@teknorapex.com

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer)	6167 RD Geleen, Netherlands	Suzhou Industrial Park	Singapore 628134
505 Central Avenue		Jiangsu, China 215126	
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com	infotaap@teknorapex.com
		infotaap@teknoapex.com	
www.teknorapex.com			

Revision Date: 5/22/2024