🚸 TEKNOR APEX

FIREGUARD® 910A-48 UVF-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle East	Latin America			
	Asia Pacific	North America			
Features	Flame Retardant	Low Smoke Emission			
	 Fungus Resistant 	• UV Resistant			
Uses	Insulation, Plenum Cable	Plenum Cable Jacketing			
Agency Ratings	• UL 13	• UL 444			
	• UL 1424	• UL QMTM2			
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS. 				
Appearance	Colors Available	• Opaque			
Forms	• Pellets				
Processing Method	Wire & Cable Extrusion				

AS	STM & ISO Properties ¹		
Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.69	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.2	MPa	ASTM D638
Tensile Elongation (Break)	250	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-10.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	4.85		
1 MHz	3.74		
Dissipation Factor			ASTM D150
1 kHz	0.064		
1 MHz	0.037		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	49	%	ASTM D2863

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Copyright © 2024 UL Prospector

FIREGUARD® 910A-48 UVF-NL Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Dynamic Heat Stability @ 205°C, 100 RPM, 76 gr. #5 Bowl (Mins. to Decomposition) : 49..... ASTM D2538

Kayeness ACR @177°C. 1000 sec-1 (Pa-sec) : 247.....ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660

- Peak Heat Release Rate (kW/m²) : 119
- Average Heat Release Rate $(kW\!/m^2):55$
- Total Heat Released (MJ/m²): 61
- Average Heat of Combustion (MJ/kg) : 10.7
- Average Specific Extinction Area (m^2/kg) : 134
- Peak Smoke (1/m): 0.7

Data Sheet Applies to Color Listed Below: Natural (1041722)

10/19-lc

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	196 °C		

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.	
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road	
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134	
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950 Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Phone: (65) 6265-2544 Fax: (65) 6265-1821	
Phone: 401-725-8000		Fax: (86) 512-6288-8371		
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com	
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com	
www.teknorapex.com				
info@teknorapex.com				

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.