

Sarlink® TPV 3190

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

SARLINK® TPV 3100 series are engineered materials designed primarily for general purpose, automotive and industrial applications requiring a good balance of thermal, mechanical, and physical properties. SARLINK® 3190, available in NAT and BLK, is a hard hardness, low density, multi-purpose thermoplastic vulcanizate that can be processed by injection molding, blow molding or extrusion for applications such as grips, seals, gaskets, profiles, hose & tubes, bellows, and other articles.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Fatigue Resistant • General Purpose • Good Adhesion • Good Flexibility	• Good Moldability • Good Processability • Good Surface Finish • Good Weather Resistance • Heat Aging Resistant	• High Hardness • Low Density • Low Specific Gravity • Resilient
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts • Automotive Under the Hood	• Blow Molding Applications • Gaskets • Industrial Applications • Profiles	• Rubber Replacement • Seals • Sheet • Weatherstripping
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	<ul style="list-style-type: none"> • CHRYSLER MS-AR-80 Type E Color: Black • CHRYSLER MS-AR-80 Type E Color: Natural • FORD WSD-M2D382-A1 Color: Black • GM QK 3526 Type 6 Color: Black • GM QK 3526 Type 6 Color: Natural • NISSAN Unspecified Color: Black • PSA Peugeot-Citroën B62 0300 version G Color: Black • RENAULT F.E.M. 03 20 007 Color: Black • VAG VW501 23 Color: Black 		
UL File Number	• QMFZ2.E54709		
Appearance	• Black	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.938	g/cm ³	ASTM D792
Density	0.940	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	6.60	MPa	
Flow : 100% Strain	10.0	MPa	
Tensile Stress			ISO 37
Across Flow : 100% Strain	6.60	MPa	
Flow : 100% Strain	10.0	MPa	
Tensile Strength			ASTM D412
Across Flow : Break	13.5	MPa	
Flow : Break	12.1	MPa	

Revision Date: 5/24/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3190

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
Across Flow : Break	13.5	MPa	
Flow : Break	12.1	MPa	
Tensile Elongation			ASTM D412
Across Flow : Break	700	%	
Flow : Break	380	%	
Tensile Elongation			ISO 37
Across Flow : Break	700	%	
Flow : Break	380	%	
Tear Strength - Across Flow	80.6	kN/m	ASTM D624
Tear Strength - Across Flow ²	81.0	kN/m	ISO 34-1
Compression Set			ASTM D395
23°C, 22 hr	48	%	
70°C, 22 hr	61	%	
125°C, 70 hr	75	%	
Compression Set			ISO 815
23°C, 22 hr	48	%	
70°C, 22 hr	61	%	
125°C, 70 hr	75	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	89		
Shore A, 5 sec, Injection Molded	92		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	89		
Shore A, 5 sec, Injection Molded	92		
Thermal	Nominal Value	Unit	Test Method
RTI Elec	50.0	°C	UL 746B
RTI Imp	50.0	°C	UL 746B
RTI Str	50.0	°C	UL 746B
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
135°C, 1000 hr	-10	%	
100% Strain, 135°C, 1000 hr	9.0	%	
150°C, 168 hr	-5.0	%	
100% Strain, 150°C, 168 hr	11	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
135°C, 1000 hr	-10	%	
100% Strain 135°C, 1000 hr	9.0	%	
150°C, 168 hr	-5.0	%	
100% Strain 150°C, 168 hr	11	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
135°C, 1000 hr	-15	%	
150°C, 168 hr	-12	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
135°C, 168 hr	-15	%	
150°C, 168 hr	-12	%	

Revision Date: 5/24/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3190

Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Durometer Hardness in Air			ASTM D573
Shore A, 135°C, 1000 hr	-1.0		
Shore A, 150°C, 168 hr	2.0		
Change in Shore Hardness in Air			ISO 188
Shore A, 135°C, 1000 hr	-1.0		
Shore A, 150°C, 168 hr	2.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	73	%	ASTM D471
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	73	%	ISO 1817
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, Natural and Black Colors)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary, @ 206/s			
200°C	310	Pa·s	ASTM D3835
200°C	310	Pa·s	ISO 11443

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	180 to 215	°C
Middle Temperature	180 to 215	°C
Front Temperature	180 to 215	°C
Nozzle Temperature	187 to 220	°C
Processing (Melt) Temp	185 to 220	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	180 to 200	°C
Cylinder Zone 2 Temp.	180 to 205	°C
Cylinder Zone 3 Temp.	187 to 210	°C
Cylinder Zone 4 Temp.	187 to 210	°C
Melt Temperature	195 to 215	°C
Die Temperature	195 to 215	°C
Take-Off Roll	20 to 50	°C

Extrusion Notes

Screen Pack: 20 to 60 mesh
Screw: general purpose
Compression Ratio: 3:1

Revision Date: 5/24/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3190

Teknor Apex Company - Thermoplastic Vulcanizate

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
<i>In U.S. for Vinyls, TPEs, Colorants,</i>	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
<i>Engineered Thermoplastics (Chem Polymer)</i> 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864	Phone: +31 46 7020 950 Fax: +31 46 7020 990	Phone: (86) 512-6287-1550 Fax: (86) 512-6288-8371	Phone: (65) 6265-2544 Fax: (65) 6265-1821
www.teknorapex.com info@teknorapex.com	www.teknorapex.com tpe@teknorapex.com	www.teknorapex.com infotaap@teknorapex.com	www.teknorapex.com infotaap@teknorapex.com

Revision Date: 5/24/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.