

Sarlink® TPV 4175

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

SARLINK® TPV 4100 series are engineered materials designed primarily for demanding automotive and industrial applications. Available in both black and natural, SARLINK® 4175 is a low density, medium hardness thermoplastic vulcanizate that exhibits excellent compression set, flex fatigue, and high and low temperature performance. The material can be processed by injection molding, blow molding and extrusion for applications such as seals, gaskets, chemical resistant hose and tube, boots and bellows.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Chemical Resistant • Excellent Elastic Recovery • Fatigue Resistant • Good Adhesion • Good Flexibility	• Good Melt Strength • Good Moldability • Good Processability • Good Surface Finish • High Melt Stability	• Low Density • Low Specific Gravity • Medium Hardness • Medium Heat Resistance • Resilient
Uses	• Agricultural Applications • Appliance Components • Automotive Applications • Automotive Interior Parts • Automotive Under the Hood	• Blow Molding Applications • Gaskets • Hose • Industrial Applications • Pipe Seals	• Profiles • Rubber Replacement • Seals • White Goods & Small Appliances
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	<ul style="list-style-type: none"> • CHRYSLER MS-AR-100 CGN Color: Black • CHRYSLER MS-AR-100 CGN Color: Natural • FORD WSD-M2D379-A6 Color: Black • FORD WSD-M2D380-A1 Color: Black • FORD WSD-M2D380-A1 Color: Natural • GM GMPE/P.003 Color: Black • GM GMPE/P.003 Color: Natural • GM GMW15813 Type 6 Color: Black • GM GMW15813 Type 6 Color: Natural • GM QK 3523 L Color: Black • GM QK 3523 L Color: Natural • PSA Peugeot-Citroën B62 0300 version G Color: Black 		
UL File Number	• QMFZ2.E54709		
Appearance	• Black	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.958	g/cm ³	ASTM D792
Density	0.960	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
Across Flow : 100% Strain	3.30	MPa	ISO 37
Across Flow : 100% Strain	3.30	MPa	ASTM D412
Flow : 100% Strain	5.30	MPa	ISO 37
Flow : 100% Strain	5.30	MPa	ASTM D412

Revision Date: 5/16/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 4175

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
Across Flow : Break	8.50	MPa	ISO 37
Across Flow : Break	8.50	MPa	ASTM D412
Flow : Break	7.20	MPa	ISO 37
Flow : Break	7.20	MPa	ASTM D412
Tensile Elongation			
Across Flow : Break	590	%	ISO 37
Across Flow : Break	590	%	ASTM D412
Flow : Break	300	%	ISO 37
Flow : Break	300	%	ASTM D412
Tear Strength - Across Flow			
--	39.0	kN/m	ASTM D624
-- ²	39.0	kN/m	ISO 34-1
Compression Set			
23°C, 22 hr	22	%	ISO 815
23°C, 22 hr	22	%	ASTM D395
70°C, 22 hr	31	%	ISO 815
70°C, 22 hr	31	%	ASTM D395
125°C, 70 hr	45	%	ISO 815
125°C, 70 hr	45	%	ASTM D395
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			
Shore A, 5 sec, Extruded	72		ISO 868
Shore A, 5 sec, Extruded	72		ASTM D2240
Shore A, 5 sec, Injection Molded	75		ISO 868
Shore A, 5 sec, Injection Molded	75		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
RTI Elec	100	°C	UL 746B
RTI Imp	65.0	°C	UL 746B
RTI Str	100	°C	UL 746B
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			
135°C, 1000 hr	-2.0	%	ISO 188
135°C, 1000 hr	-2.0	%	ASTM D573
150°C, 168 hr	-9.0	%	ISO 188
150°C, 168 hr	-9.0	%	ASTM D573
100% Strain 150°C, 168 hr	3.0	%	ISO 188
100% Strain 150°C, 168 hr	3.0	%	ASTM D573
100% Strain 150°C, 1000 hr	5.0	%	ISO 188
100% Strain 150°C, 1000 hr	5.0	%	ASTM D573
Change in Tensile Strain at Break in Air - Across Flow			
135°C, 1000 hr	-5.0	%	ISO 188
135°C, 1000 hr	-5.0	%	ASTM D573
150°C, 168 hr	-16	%	ISO 188
150°C, 168 hr	-16	%	ASTM D573

Revision Date: 5/16/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 4175

Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Shore Hardness in Air			
Shore A, 135°C, 1000 hr	2.0		ISO 188
Shore A, 135°C, 1000 hr	2.0		ASTM D573
Shore A, 150°C, 168 hr	3.0		ISO 188
Shore A, 150°C, 168 hr	3.0		ASTM D573
Change in Volume			
125°C, 70 hr, in IRM 903 Oil	78	%	ISO 1817
125°C, 70 hr, in IRM 903 Oil	78	%	ASTM D471
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.0 mm, All Colors)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	340	Pa·s	ISO 11443
200°C	340	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	138 to 160	°C
Middle Temperature	166 to 193	°C
Front Temperature	177 to 227	°C
Nozzle Temperature	182 to 227	°C
Processing (Melt) Temp	182 to 227	°C
Mold Temperature	16 to 54	°C
Injection Rate	Fast	
Back Pressure	0.345 to 1.03	MPa
Screw Speed	25 to 75	rpm
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	180 to 200	°C
Cylinder Zone 2 Temp.	180 to 205	°C
Cylinder Zone 3 Temp.	187 to 210	°C
Cylinder Zone 4 Temp.	187 to 210	°C
Melt Temperature	195 to 215	°C
Die Temperature	195 to 215	°C
Take-Off Roll	20 to 50	°C

Revision Date: 5/16/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 4175

Teknor Apex Company - Thermoplastic Vulcanizate

Extrusion Notes

Screen Pack: 20 to 60 mesh
Screw: general purpose
Compression Ratio: 3:1

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)

505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

www.teknorapex.com

info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22

6167 RD Geleen, Netherlands

Phone: +31 46 7020 950

Fax: +31 46 7020 990

www.teknorapex.com

tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550

Fax: (86) 512-6288-8371

www.teknorapex.com

infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544

Fax: (65) 6265-1821

www.teknorapex.com

infotaap@teknorapex.com

Revision Date: 5/16/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.