

# Sarlink® TPV 4180

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

## General Information

### Product Description

SARLINK® TPV 4100 series are engineered materials designed primarily for demanding automotive and industrial applications. Available in both black and natural, SARLINK® 4180 is a low density, higher hardness thermoplastic vulcanizate featuring excellent flex fatigue resistance, compression set, heat aging and resilience to be used in injection molded parts, extruded profiles, hose and tubing. It can be blow molded into boots, ducts and other articles.

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Chemical Resistant • Fatigue Resistant • Good Adhesion • Good Melt Strength • Good Moldability	• Good Processability • Good Surface Finish • Heat Aging Resistant • High Hardness • High Melt Stability	• Low Density • Low Specific Gravity • Medium Heat Resistance • Resilient
Uses	• Agricultural Applications • Appliance Components • Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts	• Automotive Under the Hood • Blow Molding Applications • Hose • Industrial Applications • Plugs	• Profiles • Rubber Replacement • Tubing • White Goods & Small Appliances
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• CHRYSLER MS-AR-100 DGN Color: Black • CHRYSLER MS-AR-100 DGN Color: Natural • FORD WSD-M2D381-A1 Color: Black • FORD WSD-M2D381-A1 Color: Natural	• GM GMP.E/P.004 Color: Black • GM GMP.E/P.004 Color: Natural • GM GMW15813 Type 7 Color: Black • GM GMW15813 Type 7 Color: Natural	• GM QK 3525 Type 5 Color: Black • GM QK 3525 Type 5 Color: Natural
UL File Number	• QMFZ2.E54709		
Appearance	• Black	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.958	g/cm <sup>3</sup>	ASTM D792
Density	0.960	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
Across Flow : 100% Strain	4.50	MPa	ISO 37
Across Flow : 100% Strain	4.50	MPa	ASTM D412
Flow : 100% Strain	6.80	MPa	ISO 37
Flow : 100% Strain	6.80	MPa	ASTM D412
Tensile Stress			
Across Flow : Break	10.2	MPa	ISO 37
Across Flow : Break	10.2	MPa	ASTM D412
Flow : Break	9.00	MPa	ISO 37
Flow : Break	9.00	MPa	ASTM D412

Revision Date: 5/15/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 4180

## Teknor Apex Company - Thermoplastic Vulcanizate

<b>Elastomers</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
<b>Tensile Elongation</b>			
Across Flow : Break	620	%	ISO 37
Across Flow : Break	620	%	ASTM D412
Flow : Break	330	%	ISO 37
Flow : Break	330	%	ASTM D412
<b>Tear Strength - Across Flow</b>			
--	48.0	kN/m	ASTM D624
-- <sup>2</sup>	48.0	kN/m	ISO 34-1
<b>Compression Set</b>			
23°C, 22 hr	26	%	ISO 815
23°C, 22 hr	26	%	ASTM D395
70°C, 22 hr	40	%	ISO 815
70°C, 22 hr	40	%	ASTM D395
125°C, 70 hr	58	%	ISO 815
125°C, 70 hr	58	%	ASTM D395
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
<b>Shore Hardness</b>			
Shore A, 5 sec, Extruded	79		ISO 868
Shore A, 5 sec, Extruded	79		ASTM D2240
Shore A, 5 sec, Injection Molded	83		ISO 868
Shore A, 5 sec, Injection Molded	83		ASTM D2240
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
RTI Elec	100	°C	UL 746B
RTI Imp	65.0	°C	UL 746B
RTI Str	100	°C	UL 746B
<b>Aging</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
<b>Change in Tensile Strength in Air - Across Flow</b>			
135°C, 1000 hr	-9.0	%	ISO 188
135°C, 1000 hr	-9.0	%	ASTM D573
100% Strain 135°C, 1000 hr	10	%	ISO 188
100% Strain 135°C, 1000 hr	10	%	ASTM D573
150°C, 168 hr	-10	%	ISO 188
150°C, 168 hr	-10	%	ASTM D573
100% Strain 150°C, 168 hr	5.0	%	ISO 188
100% Strain 150°C, 168 hr	5.0	%	ASTM D573
<b>Change in Tensile Strain at Break in Air - Across Flow</b>			
135°C, 1000 hr	-15	%	ISO 188
135°C, 1000 hr	-15	%	ASTM D573
150°C, 168 hr	-15	%	ISO 188
150°C, 168 hr	-15	%	ASTM D573
<b>Change in Shore Hardness in Air</b>			
Shore A, 135°C, 1000 hr	3.0		ISO 188
Shore A, 135°C, 1000 hr	3.0		ASTM D573
Shore A, 150°C, 168 hr	2.0		ISO 188
Shore A, 150°C, 168 hr	2.0		ASTM D573
<b>Change in Volume</b>			
125°C, 70 hr, in IRM 903 Oil	64	%	ISO 1817
125°C, 70 hr, in IRM 903 Oil	64	%	ASTM D471

Revision Date: 5/15/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 4180

## Teknor Apex Company - Thermoplastic Vulcanizate

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.0 mm, All Colors)		HB	UL 94
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	340	Pa·s	ISO 11443
200°C	340	Pa·s	ASTM D3835

### Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	82	°C
Drying Time	3.0	hr
Rear Temperature	180 to 215	°C
Middle Temperature	180 to 215	°C
Front Temperature	180 to 215	°C
Nozzle Temperature	187 to 220	°C
Processing (Melt) Temp	185 to 220	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	180 to 200	°C
Cylinder Zone 2 Temp.	180 to 205	°C
Cylinder Zone 3 Temp.	187 to 210	°C
Cylinder Zone 4 Temp.	187 to 210	°C
Melt Temperature	195 to 215	°C
Die Temperature	195 to 215	°C
Take-Off Roll	20 to 50	°C

### Extrusion Notes

Screen Pack: 20 to 60 mesh  
 Screw: general purpose  
 Compression Ratio: 3:1

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Method Ba, Angle (Unnicked)

Revision Date: 5/15/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 4180

## Teknor Apex Company - Thermoplastic Vulcanizate

### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,*

*Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

### Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan  
22  
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950  
Fax: +31 46 7020 990

[www.teknorapex.com](http://www.teknorapex.com)  
[tpe@teknorapex.com](mailto:tpe@teknorapex.com)

### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road  
Suzhou Industrial Park  
Jiangsu, China 215126

Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road  
Singapore 628134

Phone: (65) 6265-2544  
Fax: (65) 6265-1821

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 5/15/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.