

Sarlink® TPV 17175B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

The Sarlink 17100 Series is the latest generation of super high-flow TPV materials ensuring the best in class surface appearance for injection molded parts. Sarlink 17175B is a medium hardness, low density, high performance thermoplastic vulcanizate that exhibits excellent UV resistance, elasticity, and surface aesthetics designed for demanding automotive applications including window encapsulation and exterior parts.

General

Material Status	• Preliminary Data
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	<ul style="list-style-type: none"> • Chemical Resistant • Good Adhesion • Good Flexibility • Good Moldability • Good Surface Finish • High Flow • High Heat Resistance • Low Compression Set • Low Density • Low Specific Gravity • Medium Hardness • Resilient • UV Resistant
Uses	<ul style="list-style-type: none"> • Automotive Applications • Automotive Exterior Parts • Automotive Window Encapsulation • Rubber Replacement
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.921	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
Across Flow : 100% Strain	2.65	MPa	
Flow : 100% Strain	3.16	MPa	
Tensile Strength			ISO 37
Across Flow : Break	5.10	MPa	
Flow : Break	5.20	MPa	
Tensile Elongation			ISO 37
Across Flow : Break	490	%	
Flow : Break	430	%	
Tear Strength ²			ISO 34-1
Across Flow	24.7	kN/m	
Flow	23.2	kN/m	
Compression Set			ISO 815
23°C, 22 hr	26	%	
70°C, 22 hr	34	%	
125°C, 70 hr	48	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 5 sec	76		
Shore A, 15 sec	74		

Revision Date: 11/26/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 17175B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow (150°C, 168 hr)	-20	%	ISO 37
Change in Tensile Modulus in Air - Across Flow (150°C, 168 hr)	3.4	%	ISO 37
Change in Ultimate Elongation in Air - Across Flow (150°C, 168 hr)	-25	%	ISO 37
Change in Shore Hardness in Air			ISO 868
Shore A, 150°C, 168 hr ³	0.90		
Shore A, 150°C, 168 hr ⁴	1.3		

Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary, 206 l/s (200°C)	175	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	82	°C
Drying Time - Desiccant Dryer	3.0 to 4.0	hr
Dew Point - Desiccant Dryer	-40	°C
Rear Temperature	180 to 210	°C
Middle Temperature	190 to 220	°C
Front Temperature	200 to 240	°C
Nozzle Temperature	210 to 240	°C
Processing (Melt) Temp	210 to 240	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

³ 5 sec delay

⁴ 15 sec delay

Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)*
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22

6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 11/26/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.