

# Medalist® MD-12130 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Saturday, September 14, 2024

## General Information

### Product Description

The Medalist MD-12130 Series are high performance thermoplastic elastomers designed for use in medical and healthcare applications requiring high elasticity and excellent moldability. Medalist MD-12130 is a low hardness, low density grade, available in NAT and colors, which can be sterilized and exhibits excellent adhesion to polypropylene.

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Autoclave Sterilizable • Chemical Resistant • Ethylene Oxide Sterilizable • Good Adhesion • Good Colorability • Good Flexibility	• Good Moldability • Good Sterilizability • Good Toughness • Halogen Free • Low Density • Low Flow	• Low Hardness • Low Specific Gravity • Radiation (Gamma) Resistant • Resilient • Slip • Without Fillers
Uses	• Bushings • Connectors • Flexible Grips • Gaskets • Grommets	• Handles • Knobs • Medical/Healthcare Applications • Overmolding • Pharmaceuticals	• Rubber Replacement • Seals • Soft Touch Applications
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Translucent
Forms	• Pellets		
Processing Method	• Injection Molding	• Multi Injection Molding	

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.881	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (50% Strain)	0.827	MPa	ASTM D412
Tensile Stress <sup>2</sup> (100% Strain)	1.03	MPa	ASTM D412
Tensile Stress <sup>2</sup> (300% Strain)	1.65	MPa	ASTM D412
Tensile Strength <sup>2</sup> (Break)	2.79	MPa	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	540	%	ASTM D412
Tear Strength <sup>2</sup>	12.1	kN/m	ASTM D624
Compression Set <sup>3</sup>			ASTM D395
23°C, 22 hr	13	%	
70°C, 22 hr	20	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	32		
Shore A, 5 sec	30		

Revision Date: 10/11/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Medalist® MD-12130 (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

### Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	160 to 177	°C
Middle Temperature	182 to 204	°C
Front Temperature	193 to 216	°C
Nozzle Temperature	182 to 227	°C
Processing (Melt) Temp	182 to 227	°C
Mold Temperature	27 to 49	°C
Injection Rate	Fast	
Back Pressure	0.345 to 1.03	MPa
Screw Speed	50 to 100	rpm
Cushion	3.81 to 25.4	mm

### Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

For applications where adhesion or overmolding to polypropylene (PP) is required, a higher processing temperature (up to 480 °F) is recommended.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Die C, 510 mm/min

<sup>3</sup> Type 1

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,*

*Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

#### Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan  
22

6167 RD Geleen, Netherlands

Phone: +31 46 7020 950  
Fax: +31 46 7020 990

[www.teknorapex.com](http://www.teknorapex.com)  
[tpe@teknorapex.com](mailto:tpe@teknorapex.com)

#### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park  
Jiangsu, China 215126

Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

#### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544  
Fax: (65) 6265-1821

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 10/11/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.