

Medalist® MD-84348 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Saturday, September 14, 2024

General Information

Product Description

Medalist MD-84300 series are high performance thermoplastic elastomers designed specifically for extrusion and injection molded electrical applications in the medical and healthcare industry. The Medalist MD-84300 series are a better alternative to traditional TPVs used in such applications. Medalist MD-84348 is a low hardness, low density grade with good electrical properties and can be sterilized by autoclave, ETO, or gamma radiation.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Autoclave Sterilizable • Chemical Resistant • Electrically Insulating • Ethylene Oxide Sterilizable • Good Color Stability	• Good Colorability • Good Sterilizability • Halogen Free • High Tensile Strength • Low Density	• Low Flow • Low Hardness • Low Specific Gravity • Radiation Sterilizable • Slip
Uses	• Flexible Jacketing • Medical/Healthcare Applications	• Pharmaceuticals • Wire & Cable Applications	
Agency Ratings	• ISO 13485		
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	0.50	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.10	MPa	ASTM D412
Tensile Stress (300% Strain)	2.24	MPa	ASTM D412
Tensile Strength (Break)	13.4	MPa	ASTM D412
Tensile Elongation (Break)	730	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	50		
Shore A, 5 sec	48		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	ASTM D746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (136°C, 168 hr)	28	%	ASTM D573
Change in Ultimate Elongation in Air (136°C, 168 hr)	0.0	%	ASTM D573
Change in Tensile Strength			ASTM D471
60°C, 168 hr, in IRM 902 Oil	-39	%	
Change in Ultimate Elongation			ASTM D471
60°C, 168 hr, in IRM 902 Oil	-22	%	

Revision Date: 6/8/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Medalist® MD-84348 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	5.8E+16	ohms·cm	
50°C	1.1E+15	ohms·cm	
Dielectric Strength	45	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	2.23		ASTM D150
Dissipation Factor (1 kHz)	4.1E-4		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, NT)	HB		UL 94
Oxygen Index	19	%	ASTM D2863
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (200°C, 207 sec ⁻¹)	320	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	199 to 216	°C
Middle Temperature	213 to 221	°C
Front Temperature	221 to 227	°C
Nozzle Temperature	221 to 229	°C
Processing (Melt) Temp	221 to 229	°C
Mold Temperature	25 to 66	°C
Injection Pressure	1.38 to 6.89	MPa
Back Pressure	0.172 to 0.345	MPa
Screw Speed	50 to 100	rpm
Cushion	3.81 to 25.4	mm

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	193 to 210	°C
Cylinder Zone 2 Temp.	199 to 216	°C
Cylinder Zone 3 Temp.	213 to 221	°C
Cylinder Zone 4 Temp.	213 to 221	°C
Cylinder Zone 5 Temp.	221 to 227	°C
Die Temperature	221 to 229	°C

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 6/8/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Medalist® MD-84348 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road
Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road
Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 6/8/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.