

APEX® 33043RV-90NT1

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information							
General							
Material Status	Commercial: Active						
Availability	Africa & Middle East	Latin America					
	 Asia Pacific 	 North America 					
	 ADM Compliant 	Ethylene Oxide Steril	izable				
Features	• BPA Free	 Latex Free 		• Radiation (Gamma) Resistant			
reatures	 DOTP Blend Plasticizer 	 Non-Phthalate - TOT! 	M Plasticizer	 Radiation Sterilizable 			
	• E-beam Sterilizable	Non-Phthalate Plasticizer					
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS. 						
Forms	• Pellets						
Processing Method	• Extrusion						
	ASTM & IS	O Properties 1					
Physical	ASTIN & IS	Nominal Value	Unit	Test Method			
Density / Specific Gravity		1.25	g/cm³	ASTM D792			
Mechanical		Nominal Value	Unit	Test Method			
Tensile Strength				ASTM D638			
50% Strain		11.1	MPa				
100% Strain		14.9	MPa				
300% Strain		20.7	MPa				
Tensile Strength (Break)		21.2	MPa	ASTM D638			
Tensile Elongation (Break)		330	%	ASTM D638			
Hardness		Nominal Value	Unit	Test Method			
Durometer Hardness							
Durometer Hardness Shore A, 15 sec, Operating Stand		85		ASTM D2240			

Revision Date: 5/22/2024

APEX® 33043RV-90NT1

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing

Blood Transport & Delivery

Bubble Tubing

Cable Jacketing

Catheters

Dialysis Tubing

Drainage Tubing

Endotracheal Airway Tubing

Enteral Feeding Systems

Infusion Tubing

Oxygen Tubing

Peristaltic Pump Tubing

Suction Tubing

Data Sheet Applies to Color(s) Listed Below:

Clear (1136038)

Clear Blue B8 NP (1136608)

Clear Blue B6 NP (1151338)

CLEAR-NP (1136038)

10/19 Core

Processing Information

1 Tocessing Timor mation				
Extrusion	Nominal Value Unit			
Melt Temperature	174 to 185 °C			

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.teknorapex.com			

Revision Date: 5/22/2024

info@teknorapex.com