

Sarlink® TPV 6775N (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

SARLINK® TPV 6775N is a high performance thermoplastic vulcanizate used in automotive applications including interior trim. Sarlink TPV 6775N is a medium hardness, low density grade, available in Nat or can be color-matched with good color stability, exhibiting good UV resistance. This grade is designed for injection molding but could also be extruded. This grade has been approved for GM's GMW 15816 TPV Type 6 specifications and Chrysler's MS-AR-100 CMV2 specifications.

General

Material Status	• Preliminary Data		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Chemical Resistant • Good Adhesion • Good Color Stability • Good Colorability	• Light Stabilized • Low Compression Set • Low Density • Low Specific Gravity	• Medium Hardness • UV Resistant
Uses	• Automotive Applications • Automotive Interior Parts	• Automotive Interior Trim • Profiles	• Rubber Replacement • Seals
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• CHRYSLER MS-AR-100 CMV2	• GM GMW15816 Type 6	
Appearance	• Colors Available	• Opaque	• Unspecified Color
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	0.914	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	2.60	MPa	ISO 37
Tensile Stress ² (Break)	6.60	MPa	ISO 37
Tensile Elongation ² (Break)	690	%	ISO 37
Tear Strength ³	32.4	kN/m	ISO 34-1
Compression Set ⁴ (70°C, 24 hr)	40	%	ISO 815
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 5 sec, Injection Molded	78		
Shore A, 15 sec, Injection Molded	75		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	227	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Revision Date: 2/16/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 6775N (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	177 to 216	°C
Middle Temperature	177 to 216	°C
Front Temperature	177 to 216	°C
Nozzle Temperature	188 to 221	°C
Processing (Melt) Temp	182 to 221	°C
Mold Temperature	10 to 66	°C
Back Pressure	0.0689 to 1.03	MPa
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	

Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	182 to 204	°C
Cylinder Zone 2 Temp.	182 to 204	°C
Cylinder Zone 3 Temp.	188 to 210	°C
Cylinder Zone 4 Temp.	188 to 210	°C
Melt Temperature	193 to 216	°C
Die Temperature	193 to 216	°C
Take-Off Roll	21 to 49	°C

Extrusion Notes

Screen Pack: 20 to 60 mesh
Screw: 3:1 Compression Ratio

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 500 mm/min

³ Method Ba, Angle (Unnicked), 500 mm/min

⁴ Type A

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,
Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.
Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864
www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22
6167 RD Geleen, Netherlands
Phone: +31 46 7020 950
Fax: +31 46 7020 990
www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road
Suzhou Industrial Park
Jiangsu, China 215126
Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371
www.teknorapex.com
infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road
Singapore 628134
Phone: (65) 6265-2544
Fax: (65) 6265-1821
www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 2/16/2017

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.