

# Halguard® 58355

Teknor Apex Company - Polyolefin				Saturday, September 14, 202		
General Information						
General						
Material Status	• Commercial: Active					
Availability	Africa & Middle East	Latin America				
	<ul> <li>Asia Pacific</li> </ul>	North America				
Features	<ul> <li>Electrically Insulating</li> </ul>	Good Electrical Proper		Low Smoke Emission		
	• Filled	<ul> <li>Halogen Free</li> </ul>		Sunlight Resistant (720 hours)		
	Flame Retardant	<ul> <li>Low Shrinkage</li> </ul>	•	UV Stabilized		
Uses	<ul> <li>Communication Cable Jacketing</li> </ul>	<ul> <li>LSZH Insulation</li> </ul>				
	<ul> <li>Fiber Optic Cable Jacketing</li> </ul>	<ul> <li>LSZH Jacketing</li> </ul>				
Agency Ratings	• UL 94					
Regulatory Statement	<ul> <li>Due to the frequent updates to reg RoHS, please contact Teknor Ape product SDS.</li> </ul>					
Appearance	• Black	Colors Available	•	Natural Color		
Forms	• Pellets					
Processing Method	Wire & Cable Extrusion					
	ASTM & ISO	Properties <sup>1</sup>				
Physical		Nominal Value	Unit	Test Method		
Density / Specific Gravity		1.61	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (190°C/20.0 kg)		0.68	g/10 min	ASTM D1238		
Mechanical		Nominal Value	Unit	Test Method		
Tensile Strength (Break)		13.5	MPa	ASTM D638		
Tensile Elongation (Break)		120	%	ASTM D638		
Flexural Modulus		322	MPa	ASTM D790		
<b>Hardness</b>		Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D, 10 sec, Operating Stand)		50		ASTM D2240		
Thermal		Nominal Value	Unit	<b>Test Method</b>		
Continuous Use Temperature		105	°C	ASTM D794		

50°C 9.2E+13 ohms·cm Dielectric Constant (1 MHz) 3.42 ASTM D150 Dissipation Factor (1 MHz) 0.028 ASTM D150 Flammability Nominal Value Unit **Test Method** Flame Rating (1.1 mm) V-0 UL 94 Oxygen Index 43 % **ASTM D2863** 

-17.0 °C

1.5E+15 ohms·cm

Nominal Value Unit

Revision Date: 5/22/2024

ASTM D746

**Test Method** 

ASTM D257

Brittleness Temperature

Volume Resistivity

Electrical

23°C

# Halguard® 58355

## **Teknor Apex Company - Polyolefin**

#### **Additional Information**

Cone Calorimetry at 75 kW/m2 ..... ISO5660

- Peak Heat Release Rat,e (kw/m2): 83
- Total Smoke Released, (m2/m2): 416
- Average Specific Extinction Area, (m2/kg): 77

#### Acid Gas Emission

- Halogen Acid Gas Content, %: >/- 4.3 .....IEC60754-1
- pH: <0.5% ..... IEC60754-2
- Conductivity, μS/mm: </-10 ..... IEC60754-2

Post Extrusion Linear Shrinkage, %: 1.3% ..... TA Method

Data Sheet Applies to Color Listed Below: Natural (1134099)

10/22-lc

### **Processing Information**

Processing information			
Extrusion	Nominal Value Unit		
Melt Temperature	205 °C		

#### Notes

info@teknorapex.com

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.teknorapex.com			

Revision Date: 5/22/2024