

FIREGUARD® 910A-80 UVF-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information						
General						
Material Status	Commercial: Active					
Availability	Africa & Middle East	Latin America				
	 Asia Pacific 	North America				
Features	Flame Retardant	Low Smoke Emission				
	 Fungus Resistant 	• UV Resistant				
Uses	• Insulation, Plenum Cable	Plenum Cable Jacketing				
Agency Ratings	• UL 13	• UL 1424 • UL 444				
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS. 					
Appearance	Colors Available	Opaque				
Forms	• Pellets					
Processing Method	Wire & Cable Extrusion					

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.63	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	14.8	MPa	ASTM D638		
Tensile Elongation (Break)	210	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore C, 10 sec, Hand Held)	82		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	75.0	°C	ASTM D794		
Brittleness Temperature	-17.0	°C	ASTM D746		
Electrical	Nominal Value	Unit	Test Method		
Dielectric Constant			ASTM D150		
100 MHz	3.74				
250 MHz	3.68				
500 MHz	3.63				
Dissipation Factor			ASTM D150		
100 MHz	0.020				
250 MHz	0.020				
500 MHz	0.019				
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	52	%	ASTM D2863		

Revision Date: 5/22/2024

FIREGUARD® 910A-80 UVF-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Meets ICEA 696 Impact Test

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition): 39..... ASTM D2538

Kayeness ACR @ 350°F, 1000 sec-1 (Pa-sec): 378..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660
• Peak Heat Release Rate (kW/m²): 118.0
• Average Heat Release Rate (kW/m²): 64.7

• Total Heat Released (MJ/m²): 78.5

Average Heat of Combustion (MJ/kg): 12.4
 Average Specific Extinction Area (m²/kg): 243

• Peak Smoke (1/m): 1.3

Data Sheet Applied to Color Listed Below: Natural (1103832)

5/22-lc

Processing InformationExtrusionNominal ValueUnitMelt Temperature196 °C

Notes

info@teknorapex.com

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.teknorapex.com			

Revision Date: 5/22/2024