TEKNOR APEX

Halguard[®] 58620

Teknor Apex Company - Polyolefin

Saturday, September 14, 2024

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle East	Latin America			
	Asia Pacific	North America			
Features	Electrically Insulating	Good Electrical Properties	Low Smoke Emission		
	• Filled	Halogen Free	 Sunlight Resistant (720 hours) 		
	Flame Retardant	Low Shrinkage	UV Stabilized		
Uses	Communication Cable Jacketing	LSZH Insulation			
	Fiber Optic Cable Jacketing	 LSZH Jacketing 			
Agency Ratings	• UL 94	• UL AATJ2			
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.				
Appearance	• Black	Finishes Available	Natural Color		
Forms	• Pellets				
Processing Method	Wire & Cable Extrusion				

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.57	g/cm ³	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/20.0 kg)	6.8	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	13.1	MPa	ASTM D638	
Tensile Elongation (Break)	170	%	ASTM D638	
Flexural Modulus	148	MPa	ASTM D790	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D, 10 sec, Operating Stand)	48		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	105	°C	ASTM D794	
Brittleness Temperature	-43.0	°C	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity			ASTM D257	
23°C	1.8E+15	ohms·cm		
50°C	1.7E+14	ohms·cm		
Dielectric Constant (1 MHz)	3.76		ASTM D150	
Dissipation Factor (1 MHz)	0.018		ASTM D150	
Flammability	Nominal Value	Unit	Test Method	
Flame Rating (1.6 mm)	V-1		UL 94	
Oxygen Index	40	%	ASTM D2863	

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Halguard® 58620 Teknor Apex Company - Polyolefin

Additional Information

Post extrusion Linear Shrinkage: 1.3% TA Test Method

Cone Calorimetry at 75 kW/m2 ISO5660

- Peak Heat Release Rate, (kw/m2): 162
- Total Smoke Released, (m2/m2): 1,454
- Average Specific Extinction Area, (m2/kg): 259

Deformation at 121C, % (0.060" thick specimens): 1% UL1581

Data Sheet Applies to Color Listed Below: Natural (1084028)

11/19-lc

Processing Information		
Extrusion	Nominal Value Unit	
Melt Temperature	193 °C	

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950	-	Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com

www.teknorapex.com info@teknorapex.com

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.