

Halguard® 58240

Teknor Apex Company - Polyolefin

Saturday, September 14, 2024

General Information

General

| | | | |
|----------------------|--|--|---|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Latin America • North America | |
| Features | • Electrically Insulating • Filled • Flame Retardant | • Good Electrical Properties • Halogen Free • Low Smoke Emission | • Sunlight Resistant (720 hours) • UV Stabilized |
| Uses | • LSZH Insulation | • LSZH Jacketing | |
| Agency Ratings | • UL 94 | • UL AATJ2 | |
| Regulatory Statement | • Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS. | | |
| Appearance | • Black | • Colors Available | • Natural Color |
| Forms | • Pellets | | |
| Processing Method | • Wire & Cable Extrusion | | |

ASTM & ISO Properties¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|-------------------|-------------|
| Density / Specific Gravity | 1.60 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (190°C/20.0 kg) | 3.8 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 14.8 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 160 | % | ASTM D638 |
| Flexural Modulus | 80.7 | MPa | ASTM D790 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D, 10 sec, Operating Stand) | 42 | | ASTM D2240 |
| Thermal | Nominal Value | Unit | Test Method |
| Continuous Use Temperature | 105 | °C | ASTM D794 |
| Brittleness Temperature | -42.0 | °C | ASTM D746 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | | | ASTM D257 |
| 23°C | 6.7E+15 | ohms·cm | |
| 50°C | 4.5E+14 | ohms·cm | |
| Dielectric Constant (1 MHz) | 3.44 | | ASTM D150 |
| Dissipation Factor (1 MHz) | 0.021 | | ASTM D150 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (1.6 mm) | V-0 | | UL 94 |
| Oxygen Index | 43 | % | ASTM D2863 |

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Halguard® 58240

Teknor Apex Company - Polyolefin

Additional Information

Cone Calorimetry at 75 kW/m² ISO5660

- Peak Heat Release Rate, (kW/m²): 97
- Total Smoke Released, (m²/m²): 680
- Average Specific Extinction Area (m²/kg): 123

Acid Gas Emission

Halogen Acid Gas Content, %: <0.5% IEC60754-1

pH: >/-4.3 IEC60754-2

Conductivity, μS/mm: </-10 IEC60754-2

Deformation at 121C, % (0.060" thick specimens): 6.6% UL1581

720 Hour Sunlight Resistance (0.20 thick specimens): Pass UL1581

Data Sheet Applies to Color Listed Below:

Natural (1134736)

1/20-lc

Processing Information

Extrusion

Nominal Value Unit

Melt Temperature

204 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000

Fax: 401-725-8095

Toll Free (U.S. only) 800-556-3864

www.teknorapex.com

info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22

6167 RD Geleen, Netherlands

Phone: +31 46 7020 950

Fax: +31 46 7020 990

www.teknorapex.com

tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550

Fax: (86) 512-6288-8371

www.teknorapex.com

infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544

Fax: (65) 6265-1821

www.teknorapex.com

infotaap@teknorapex.com

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.