

# Halguard® 58242

Teknor Apex Company - Polyolefin

Saturday, September 14, 2024

## General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Additive	• Lubricant	• Metal Deactivator	• UV Stabilizer
Features	• Electrically Insulating • Filled • Flame Retardant	• Good Electrical Properties • Halogen Free • Low Smoke Emission	• Sunlight Resistant (720 hours) • UV Stabilized
Uses	• LSZH Insulation	• LSZH Jacketing	
Agency Ratings	• UL 94	• UL AATJ2	
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

## ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.57	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/20.0 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	15.7	MPa	ASTM D638
Tensile Elongation (Break)	170	%	ASTM D638
Flexural Modulus	94.5	MPa	ASTM D790
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 10 sec, Operating Stand	41		
Shore D, 10 sec, Hand Held	46		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	ASTM D794
Brittleness Temperature	-33.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	6.5E+15	ohms·cm	
50°C	1.2E+15	ohms·cm	
Dielectric Constant (1 MHz)	3.39		ASTM D150
Dissipation Factor (1 MHz)	0.020		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm)	V-0		UL 94
Oxygen Index	41	%	ASTM D2863

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Halguard® 58242

## Teknor Apex Company - Polyolefin

### Additional Information

Cone Calorimetry @ 75 kW/m<sup>2</sup> ..... ISO5660

- Peak Heat Release Rate (kW/m<sup>2</sup>) : 96
- Total Smoke Released (m<sup>2</sup>/m<sup>2</sup>) : 687
- Average Specific Extinction Area, (m<sup>2</sup>/kg) : 129

Deformation at 121°C, % (0.060" thick specimens) : 9.1% ..... UL1581

720 Hour Sunlight Resistance (0.20" thick specimens) : PASS ..... UL1581

Data Sheet Applies to Colors Listed Below:

Natural (1135439)  
Blue 2344 (1137662)  
Red 1191 (1139335)

11/19-1c

### Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	205	°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,*  
*Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.  
  
Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

#### Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan  
22  
6167 RD Geleen, Netherlands  
  
Phone: +31 46 7020 950  
Fax: +31 46 7020 990  
  
[www.teknorapex.com](http://www.teknorapex.com)  
[tpe@teknorapex.com](mailto:tpe@teknorapex.com)

#### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road  
Suzhou Industrial Park  
Jiangsu, China 215126  
  
Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371  
  
[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

#### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road  
Singapore 628134  
  
Phone: (65) 6265-2544  
Fax: (65) 6265-1821  
  
[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.