

FIREGUARD® 910A-70 UVF-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information				
General				
Material Status	Commercial: Active			
Availability	Africa & Middle East	Latin America		
	 Asia Pacific 	North America		
Features	Flame Retardant	Low Smoke Emission		
	 Fungus Resistant 	• UV Resistant		
Uses	Insulation, Plenum Cable	Plenum Cable Jacketing		
Agency Ratings	• UL 13	• UL 444		
	• UL 1424	• UL QMTM2		
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, ar RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of product SDS. 			
Appearance	Colors Available	• Opaque		
Forms	• Pellets			
Processing Method	Wire & Cable Extrusion			

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.68	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	15.6	MPa	ASTM D638		
Tensile Elongation (Break)	320	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore C, 10 sec, Hand Held)	77		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	75.0	°C	ASTM D794		
Brittleness Temperature	-16.0	°C	ASTM D746		
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	58	%	ASTM D2863		
Additional Information					

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition): 22..... ASTM D2538

Kayeness ACR @177°C. 1000 sec-1 (Pa-sec): 379.....ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660

• Peak Heat Release Rate (kW/m²): 82.7

 $\bullet \ \ Average \ Heat \ Release \ Rate \ (kW/m^2): 39.9$

• Total Heat Released (MJ/m²) :43.6

• Average Heat of Combustion (MJ/kg) : 7.8

• Average Specific Extinction Area (m²/kg): 63.9

• Peak Smoke (1/m): 0.7

Data Sheet Applies to Colors Listed Below:

Natural (1069028)

Blue 2084 (1070486)

10/19-1c

Revision Date: 5/22/2024

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

FIREGUARD® 910A-70 UVF-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information

1 Toccssing Throt mation		
Extrusion	Nominal Value Unit	
Melt Temperature	196 °C	

Notes

info@teknorapex.com

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.teknorapex.com			

Revision Date: 5/22/2024