

FIREGUARD® 910A-67-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General Information					
General					
Material Status	Commercial: Active				
A 9.195	Africa & Middle East	Latin America			
Availability	 Asia Pacific 	North America			
Features	Flame Retardant	Low Smoke Emission			
Uses	Insulation, Plenum Cable	Plenum Cable Jacketing			
	• UL 13	• UL 444			
Agency Ratings	• UL 1424	• UL QMTM2			
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, an RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of product SDS. 				
Appearance	Colors Available	• Opaque			
Forms	• Pellets				
Processing Method	Wire & Cable Extrusion				

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.66	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	15.7	MPa	ASTM D638		
Tensile Elongation (Break)	210	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore C, 10 sec, Hand Held)	88		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	75.0	°C	ASTM D794		
Brittleness Temperature	-2.00	°C	ASTM D746		
Electrical	Nominal Value	Unit	Test Method		
Dielectric Constant			ASTM D150		
1 kHz	4.63				
1 MHz	3.64				
Dissipation Factor			ASTM D150		
1 kHz	0.090				
1 MHz	0.034				
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	55	%	ASTM D2863		

Revision Date: 5/22/2024

FIREGUARD® 910A-67-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition): 28..... ASTM D2538

Kayeness ACR @ 350°F, 1000 sec-1 (Pa-sec) : 341..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660
• Peak Heat Release Rate (kW/m²): 111.8
• Average Heat Release Rate (kW/m²): 59.8
• Total Heat Released (MJ/m²): 71.4

Average Heat of Combustion (MJ/kg): 11.5
 Average Specific Extinction Area (m²/kg): 204

• Peak Smoke (1/m): 1.43

Data Sheet Applies to Color Listed Below: Natural (1066210)

10/19-lc

Processing Information				
Extrusion	Nominal Value Unit			
Melt Temperature	196 °C			

Notes

info@teknorapex.com

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950	DI (00) 540 0007 4550	Phone: (65) 6265-2544
Phone: 401-725-8000	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550 Fax: (86) 512-6288-8371	Fax: (65) 6265-1821
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.teknorapex.com			

Revision Date: 5/22/2024