

FIREGUARD® 910A-10-NL2

Teknor Apex Company - Flexible Polyvinyl Chloride

Saturday, September 14, 2024

General					
Material Status	Commercial: Active				
Availability	Africa & Middle East	Latin America			
	 Asia Pacific 	North America			
Features	• Flame Retardant	 Low Smoke Emission 			
Uses	• Insulation, Plenum Cable	Plenum Cable Jacketi	ng		
Agency Ratings	• UL 13	• UL 444			
	• UL 1424	• UL QMTM2			
Regulatory Statement	 Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS. 				
Appearance	Colors Available	• Opaque			
Forms	• Pellets				
Processing Method	Wire & Cable Extrusion				
	ASTM & IS	O Properties ¹			
Physical		Nominal Value	Unit	Test Method	
Density / Specific Gravity		1.59	g/cm³	ASTM D792	
Mechanical		Nominal Value	Unit	Test Method	
Tensile Strength (Break)		17.9	MPa	ASTM D638	
Tensile Elongation (Break)		200	%	ASTM D638	
Hardness		Nominal Value	Unit	Test Method	
Durometer Hardness				ASTM D2240	
Shore C, 10 sec, Hand Held		87			
Shore D, 10 sec, Operating Stand		62			
Thermal		Nominal Value	Unit	Test Method	
Continuous Use Temperature		75.0	°C	ASTM D794	
Brittleness Temperature		-4.00	°C	ASTM D746	
Electrical		Nominal Value	Unit	Test Method	
Dielectric Constant				ASTM D150	
1 kHz		4.57			
1 MHz		3.52			
				ASTM D150	
Dissipation Factor					
Dissipation Factor 1 kHz		0.069			
•		0.069 0.045			

General Information

Revision Date: 5/22/2024

FIREGUARD® 910A-10-NL2

Teknor Apex Company - Flexible Polyvinyl Chloride

Dynamic Heat Stability @ 205°C, 100 RPM, 72 gr. #5 Bowl (Mins. to Decomposition): 31....ASTM D2538

Kayeness ACR @ 370°F, 1000 sec-1 (Pa-sec) : 295..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660

• Peak Heat Release Rate (kW/m²): 108

• Average Heat Release Rate (kW/m²): 65

• Total Heat Released (MJ/m²): 64

• Average Heat of Combustion (MJ/kg): 10.2

• Average Specific Extinction Area (m²/kg): 425

• Peak Smoke (1/m): 2.5

Data Sheet Applies to Colors Listed Below:

Natural (0109775)

White 1398 (1070944)

Black 755 (1138421)

Blue 2105 (1056863)

Blue 2180 (1071920)

Blue 2350 (1138390)

Grey 2960 (1056893)

10/19-lc

Processing Information				
Extrusion	Nominal Value Unit			
Melt Temperature	196 ℃			

Notes

¹ Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants,	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
Engineered Thermoplastics (Chem Polymer) 505 Central Avenue	6167 RD Geleen, Netherlands	Suzhou Industrial Park Jiangsu, China 215126	Singapore 628134
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950		Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000		Fax: (86) 512-6288-8371	
Fax: 401-725-8095	www.teknorapex.com		www.teknorapex.com
Toll Free (U.S. only) 800-556-3864	tpe@teknorapex.com	www.teknorapex.com infotaap@teknoapex.com	infotaap@teknorapex.com
www.toknoranov.com			

Revision Date: 5/22/2024

info@teknorapex.com