

Sarlink® TPV 5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

The Sarlink TPV 5700B series are highly engineered extrusion-grade thermoplastic vulcanizates with outstanding UV stability designed for demanding automotive interior and exterior sealing applications, including glass run channels, waistbelts, weather strips, seals and other profiles. Sarlink TPV 5740DB is a high hardness, medium density, high performance grade with low fogging and excellent color retention and elastic properties.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Chemical Resistant • High Hardness • High Heat Resistance	• High Tensile Strength • Low Compression Set • Medium Density	• Resilient • UV Resistant
Uses	• Automotive Applications • Belts/Belt Repair	• Profiles • Rubber Replacement	• Seals • Weatherstripping
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• BMW Mini/BMW Unspecified Color: Black • GM GMW15812, Type 9 Color: Black • PSA Peugeot-Citroën B62 0300 version G Color: Black • TOYOTA TSM 5746G-1 Color: Black		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Blow Molding • Extrusion	• Injection Molding • Profile Extrusion	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.958	g/cm ³	ASTM D792
Density	0.960	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	9.03	MPa	
Flow : 100% Strain	13.3	MPa	
Tensile Stress			ISO 37
Across Flow : 100% Strain	9.00	MPa	
Flow : 100% Strain	13.3	MPa	
Tensile Strength			ASTM D412
Across Flow : Break	19.0	MPa	
Flow : Break	18.0	MPa	
Tensile Stress			ISO 37
Across Flow : Break	19.0	MPa	
Flow : Break	18.0	MPa	
Tensile Elongation			ASTM D412
Across Flow : Break	640	%	
Flow : Break	490	%	
Tensile Elongation			ISO 37
Across Flow : Break	640	%	
Flow : Break	490	%	

Revision Date: 1/11/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tear Strength - Across Flow	87.6	kN/m	ASTM D624
Tear Strength - Across Flow ²	88.0	kN/m	ISO 34-1
Compression Set			ASTM D395
23°C, 22 hr	46	%	
70°C, 22 hr	58	%	
125°C, 70 hr	80	%	
Compression Set			ISO 815
23°C, 22 hr	46	%	
70°C, 22 hr	58	%	
125°C, 70 hr	80	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 5 sec, Extruded	38		
Shore D, 5 sec, Injection Molded	40		
Shore Hardness			ISO 868
Shore D, 5 sec, Extruded	38		
Shore D, 5 sec, Injection Molded	40		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
135°C, 1000 hr	-20	%	
100% Strain, 135°C, 1000 hr	9.0	%	
150°C, 168 hr	-22	%	
100% Strain, 150°C, 168 hr	5.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
135°C, 1000 hr	-20	%	
100% Strain 135°C, 1000 hr	9.0	%	
150°C, 168 hr	-22	%	
100% Strain 150°C, 168 hr	5.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
135°C, 1000 hr	-25	%	
150°C, 168 hr	-25	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
135°C, 1000 hr	-25	%	
150°C, 168 hr	-25	%	
Change in Durometer Hardness in Air			ASTM D573
Shore D, 135°C, 1000 hr	3.0		
Shore D, 150°C, 168 hr	3.0		
Change in Shore Hardness in Air			ISO 188
Shore D, 135°C, 1000 hr	3.0		
Shore D, 150°C, 168 hr	3.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	47	%	ASTM D471
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	47	%	ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	400	Pa·s	ASTM D3835
200°C	400	Pa·s	ISO 11443

Revision Date: 1/11/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 5740DB

Teknor Apex Company - Thermoplastic Vulcanizate

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	177 to 216	°C
Middle Temperature	177 to 216	°C
Front Temperature	177 to 216	°C
Nozzle Temperature	188 to 221	°C
Processing (Melt) Temp	182 to 221	°C
Mold Temperature	10 to 66	°C
Back Pressure	0.0689 to 1.03	MPa
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	

Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	182 to 204	°C
Cylinder Zone 2 Temp.	182 to 204	°C
Cylinder Zone 3 Temp.	188 to 210	°C
Cylinder Zone 4 Temp.	188 to 210	°C
Melt Temperature	193 to 216	°C
Die Temperature	193 to 216	°C
Take-Off Roll	21 to 49	°C

Extrusion Notes

Screen Pack: 20 to 60 mesh
Screw: 3:1 Compression Ratio

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
<i>In U.S. for Vinyls, TPEs, Colorants,</i>	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
<i>Engineered Thermoplastics (Chem Polymer)</i>	6167 RD Geleen, Netherlands	Suzhou Industrial Park	Singapore 628134
505 Central Avenue		Jiangsu, China 215126	
Pawtucket, Rhode Island 02861 U.S.	Phone: +31 46 7020 950	Phone: (86) 512-6287-1550	Phone: (65) 6265-2544
	Fax: +31 46 7020 990	Fax: (86) 512-6288-8371	Fax: (65) 6265-1821
Phone: 401-725-8000	www.teknorapex.com	www.teknorapex.com	www.teknorapex.com
Fax: 401-725-8095	tpe@teknorapex.com	infotaap@teknorapex.com	infotaap@teknorapex.com
Toll Free (U.S. only) 800-556-3864			
www.teknorapex.com			
info@teknorapex.com			

Revision Date: 1/11/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.