

Sarlink® TPV 4775B42

Teknor Apex Company - Thermoplastic Vulcanizate

Saturday, September 14, 2024

General Information

Product Description

The Sarlink TPV 4700 Series are very high flow injection molding engineering grades with excellent UV resistance, elasticity, and surface aesthetics designed for demanding automotive applications including window encapsulation and exterior parts. Sarlink® TPV 4775B42 is a black, medium hardness, low density thermoplastic vulcanizate suited for injection molding applications that require superior flow properties.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe Latin America North America
Features	<ul style="list-style-type: none"> Chemical Resistant Good Flexibility Good Processability Good Weather Resistance High Flow Low Density Low Specific Gravity Medium Hardness Resilient UV Resistant
Uses	<ul style="list-style-type: none"> Automotive Applications Automotive Exterior Parts Automotive Window Encapsulation Rubber Replacement
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant
Automotive Specifications	<ul style="list-style-type: none"> BMW Unspecified Color: Black DAIMLER DBL 5422 Color: Black DAIMLER DBL 5562.30 Color: Black FORD WSS-M9P-10A Color: Black GM QK 3523 L Color: Black HONDA 73512-T6L Color: Black PSA Peugeot-Citroën B62 0300 version G Color: Black RENAULT 32 06 41 D Color: Black TOYOTA TSM 1707G-7 Color: Black VAG VW501 23 Color: Black VAG VW-TL 52381-C Color: Black VOLKSWAGEN VW 50180 Color: Black
Appearance	<ul style="list-style-type: none"> Black
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.908	g/cm ³	ASTM D792
Density	0.910	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	3.20	MPa	
Flow : 100% Strain	3.40	MPa	
Tensile Stress			ISO 37
Across Flow : 100% Strain	3.20	MPa	
Flow : 100% Strain	3.40	MPa	
Tensile Strength			ASTM D412
Across Flow : Break	6.30	MPa	
Flow : Break	5.80	MPa	
Tensile Stress			ISO 37
Across Flow : Break	6.30	MPa	
Flow : Break	5.80	MPa	

Revision Date: 10/22/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 4775B42

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tensile Elongation			ASTM D412
Across Flow : Break	470	%	
Flow : Break	410	%	
Tensile Elongation			ISO 37
Across Flow : Break	470	%	
Flow : Break	410	%	
Tear Strength - Across Flow	31.5	kN/m	ASTM D624
Tear Strength - Across Flow ²	31.0	kN/m	ISO 34-1
Compression Set			ASTM D395
23°C, 22 hr	24	%	
70°C, 22 hr	39	%	
100°C, 22 hr	48	%	
125°C, 70 hr	56	%	
Compression Set			ISO 815
23°C, 22 hr	24	%	
70°C, 22 hr	39	%	
100°C, 22 hr	48	%	
125°C, 70 hr	56	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	74		
Shore A, 5 sec, Injection Molded	76		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	74		
Shore A, 5 sec, Injection Molded	76		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
135°C, 1000 hr	-18	%	
100% Strain, 135°C, 1000 hr	3.0	%	
150°C, 168 hr	-19	%	
100% Strain, 150°C, 168 hr	2.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
135°C, 1000 hr	-18	%	
100% Strain 135°C, 1000 hr	3.0	%	
150°C, 168 hr	-19	%	
100% Strain 150°C, 168 hr	2.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
135°C, 1000 hr	-28	%	
150°C, 168 hr	-24	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
135°C, 1000 hr	-28	%	
150°C, 168 hr	-24	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 135°C, 1000 hr	-2.0		
Shore A, 150°C, 168 hr	1.0		
Change in Shore Hardness in Air			ISO 188
Shore A, 135°C, 1000 hr	-2.0		
Shore A, 150°C, 168 hr	1.0		

Revision Date: 10/22/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 4775B42

Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	73	%	ASTM D471
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	73	%	ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	200	Pa·s	ASTM D3835
200°C	200		ISO 11443

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	82	°C
Drying Time - Desiccant Dryer	3.0 to 4.0	hr
Dew Point - Desiccant Dryer	-40	°C
Suggested Shot Size	25 to 50	%
Rear Temperature	180 to 210	°C
Middle Temperature	190 to 220	°C
Front Temperature	200 to 240	°C
Nozzle Temperature	210 to 240	°C
Processing (Melt) Temp	210 to 240	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm

Extrusion Notes

Spiral Flow Ratio, DSM Method: 3

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
<i>In U.S. for Vinyls, TPEs, Colorants,</i>	Brightlands Chemelot Campus Umonderbaan 22	No. 78 Ping Sheng Road	41 Shipyard Road
<i>Engineered Thermoplastics (Chem Polymer)</i>	6167 RD Geleen, Netherlands	Suzhou Industrial Park	Singapore 628134
505 Central Avenue	Phone: +31 46 7020 950	Jiangsu, China 215126	Phone: (65) 6265-2544
Pawtucket, Rhode Island 02861 U.S.	Fax: +31 46 7020 990	Phone: (86) 512-6287-1550	Fax: (65) 6265-1821
Phone: 401-725-8000	www.teknorapex.com	Fax: (86) 512-6288-8371	www.teknorapex.com
Fax: 401-725-8095	tpe@teknorapex.com	www.teknorapex.com	infotaap@teknorapex.com
Toll Free (U.S. only) 800-556-3864		infotaap@teknorapex.com	
www.teknorapex.com			
info@teknorapex.com			

Revision Date: 10/22/2023

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.